



Material Composition Sheet

Product: GS1540-CQRE3
 Package Type: DQFP-128 pin (66/tray)
 Manufacturer: Gennum Corporation

Date: 06-Dec-2006

Component	BOM	Weight of Component (mg)	Substance	Weight of Substance (mg)	Homogeneous Material	
					%	ppm
Chip		9.24	Al	0.06	0.64	6494
			Si	9.18	99.35	993506
			Sub-total:	9.24	99.99	1000000
Die Attach	CRM 1076DS	3.81	Ag	2.89	75.85	758530
			Epoxy Resin	0.49	12.86	128609
			Epoxy Silane	0.05	1.31	13123
			Phenol Resin	0.11	2.88	28871
			t-Butylphenylglycidil ether	0.27	7.08	70866
			Sub-total:	3.81	99.98	999999
Lead Finish External		31.50	Sn	31.50	100.00	1000000
			Sub-total:	31.50	100.00	1000000
Lead Finish Internal		1.16	Ag	1.16	100.00	1000000
			Sub-total:	1.16	100.00	1000000
Leadframe	OLIN 7025	270.80	Cu	260.51	96.20	962001
			Mg	0.41	0.15	1514
			Ni	8.12	2.99	29985
			Si	1.76	0.64	6499
			Sub-total:	270.80	99.98	999999
Marking Ink	Teca 261	0.10		0.00	0.00	0
			Sub-total:	0.00	0.00	0
Mold Compound	EME G700	1421.81	Carbon Black	7.11	0.50	5001
			Epoxy Resin	113.74	7.99	79997
			Phenol Resin	92.42	6.50	65002
			SiO2	1208.54	85.00	850001
			Sub-total:	1421.81	99.99	1000001
Wires	MGM7	2.40	Au	2.40	100.00	1000000
			Sub-total:	2.40	100.00	1000000
Total:		1740.82				

GENNUM CORPORATION

Mailing Address: P.O. Box 489, Stn. A, Burlington, Ontario, Canada L7R 3Y3
 Shipping Address: 970 Fraser Drive, Burlington, Ontario, Canada L7L 5P5
 Tel. +1 (905) 632-2996 Fax. +1 (905) 632-5946

www.gennum.com

The information contained in this document describes the homogeneous material composition of this product according to the definition set forth in the EU RoHS Directive 2002/95/EC. This information may have been derived from calculations based on information obtained from our suppliers. Gennum Corporation assumes no liability for any errors or omissions in this document. Gennum reserves the right to make changes to this document at any time without notice.