



Material Composition Sheet

Product: GS4900BCNE3
 Package Type: QFN-64 pin (160/tray)
 Manufacturer: Gennum Corporation

Date: 06-Dec-2006

Component	BOM	Weight of Component (mg)	Substance	Weight of Substance (mg)	Homogeneous Material	
					%	ppm
Die		7.79	Al	0.05	0.64	6418
			Si	7.74	99.35	993582
			Sub-total:	7.79	99.99	1000000
Die Attach	CRM 1076DS	1.17	Ag	0.90	76.92	769231
			Epoxy Resin	0.15	12.82	128205
			Epoxy Silane	0.01	0.85	8547
			Phenol Resin	0.03	2.56	25641
			t-Butylphenylglycidil ether	0.08	6.83	68376
			Sub-total:	1.17	99.98	1000000
Internal Pad Plating		1.69	Ag	1.69	100.00	1000000
			Sub-total:	1.69	100.00	1000000
Leadframe	Olin 7025	117.14	Cu	112.69	96.20	962011
			Mg	0.18	0.15	1537
			Ni	3.51	2.99	29964
			Si	0.76	0.64	6488
			Sub-total:	117.14	99.98	1000000
Marking Ink		0.00		0.00	0.00	0
			Sub-total:	0.00	0.00	0
Mold Compound	EME G770HC	102.53	Carbon Black	0.51	0.49	4974
			Epoxy Resin A	4.61	4.49	44962
			Epoxy Resin B	4.61	4.49	44962
			Metal Hydroxide	2.05	1.99	19994
			Phenol Resin	4.61	4.49	44962
			SiO2	86.14	84.01	840144
			Sub-total:	102.53	99.96	999998
Terminals Finish		5.26	Au	5.26	100.00	1000000
			Sub-total:	5.26	100.00	1000000
Wires	AW88	1.79	Au	1.79	100.00	1000000
			Sub-total:	1.79	100.00	1000000
Total:		237.37				

GENNUM CORPORATION

Mailing Address: P.O. Box 489, Stn. A, Burlington, Ontario, Canada L7R 3Y3
 Shipping Address: 970 Fraser Drive, Burlington, Ontario, Canada L7L 5P5
 Tel. +1 (905) 632-2996 Fax. +1 (905) 632-5946

www.gennum.com

The information contained in this document describes the homogeneous material composition of this product according to the definition set forth in the EU RoHS Directive 2002/95/EC. This information may have been derived from calculations based on information obtained from our suppliers. Gennum Corporation assumes no liability for any errors or omissions in this document. Gennum reserves the right to make changes to this document at any time without notice.