



## Material Composition Sheet

Product: GS9004DCKB  
 Package Type: SOIC-14 (57/tube)  
 Manufacturer: Gennum Corporation

Date: 11-Dec-2006

Component	BOM	Weight of Component (mg)	Substance	Weight of Substance (mg)	Homogeneous Material	
					%	ppm
Chip		3.06	Al	0.02	0.65	6536
			Si	3.04	99.34	993464
			Sub-total:	3.06	99.99	1000000
Die Attach	84-1 LMISR4	0.29	Aromatic Amine	0.02	6.89	68966
			Epoxy Resin	0.05	17.24	172414
			Silver	0.22	75.86	758621
			Sub-total:	0.29	99.99	1000001
Lead Finish External		2.24	Pb	0.56	25.00	250000
			Sn	1.68	75.00	750000
			Sub-total:	2.24	100.00	1000000
Lead Finish Internal		0.21	Ag	0.21	100.00	1000000
			Sub-total:	0.21	100.00	1000000
Leadframe	Olin 194FH	43.03	Cu	41.96	97.51	975134
			Fe	1.01	2.34	23472
			P	0.01	0.02	232
			Zn	0.05	0.11	1162
			Sub-total:	43.03	99.98	1000000
Marking Ink	Wieder W238	0.00		0.00	0.00	0
			Sub-total:	0.00	0.00	0
Mold Compound	EME 6300H	78.93	Antimony Trioxide	2.37	3.00	30027
			BrominatedEpoxyResin	1.58	2.00	20018
			Carbon Black	0.24	0.30	3041
			Epoxy Cresol Novolac	12.63	16.00	160015
			Phenol/Novolac resin	4.50	5.70	57013
			Silica Fused	57.61	72.98	729887
			Sub-total:	78.93	99.98	1000001
Wires	SGA3	0.27	Au	0.27	100.00	1000000
			Sub-total:	0.27	100.00	1000000
<b>Total:</b>		<b>128.03</b>				

### GENNUM CORPORATION

Mailing Address: P.O. Box 489, Stn. A, Burlington, Ontario, Canada L7R 3Y3  
 Shipping Address: 970 Fraser Drive, Burlington, Ontario, Canada L7L 5P5  
 Tel. +1 (905) 632-2996 Fax. +1 (905) 632-5946

[www.gennum.com](http://www.gennum.com)

The information contained in this document describes the homogeneous material composition of this product according to the definition set forth in the EU RoHS Directive 2002/95/EC. This information may have been derived from calculations based on information obtained from our suppliers. Gennum Corporation assumes no liability for any errors or omissions in this document. Gennum reserves the right to make changes to this document at any time without notice.