



Material Composition Sheet

Product: GS9010ACKC
 Package Type: SOIC-16W (47/tube)
 Manufacturer: Gennum Corporation

Date: 06-Dec-2006

Component	BOM	Weight of Component (mg)	Substance	Weight of Substance (mg)	Homogeneous Material	
					%	ppm
Chip		8.02	Al	0.05	0.62	6234
			Si	7.97	99.37	993766
			Sub-total:	8.02	99.99	1000000
Die Attach	84-1 LMISR4	1.33	Aromatic Amine	0.07	5.26	52632
			Epoxy Resin	0.23	17.29	172932
			Silver	1.03	77.44	774436
			Sub-total:	1.33	99.99	1000000
Lead Finish External		2.83	Pb	0.71	25.08	250883
			Sn	2.12	74.91	749117
			Sub-total:	2.83	99.99	1000000
Lead Finish Internal		0.27	Ag	0.27	100.00	1000000
			Sub-total:	0.27	100.00	1000000
Leadframe	Olin 194FH	120.51	Cu	117.50	97.50	975023
			Fe	2.83	2.34	23484
			P	0.04	0.03	332
			Zn	0.14	0.11	1162
			Sub-total:	120.51	99.98	1000001
Marking Ink	Wieder W238	0.01		0.00	0.00	0
			Sub-total:	0.00	0.00	0
Mold Compound	EME 6300H	286.45	Antimony Trioxide	8.59	2.99	29988
			BrominatedEpoxyResin	5.73	2.00	20003
			Carbon Black	0.86	0.30	3002
			Epoxy Cresol Novolac	45.83	15.99	159993
			Phenol/Novolac resin	16.33	5.70	57008
			Silica Fused	209.11	73.00	730005
			Sub-total:	286.45	99.98	999999
Wires	SGA3	0.78	Au	0.78	100.00	1000000
			Sub-total:	0.78	100.00	1000000
Total:		420.20				

GENNUM CORPORATION

Mailing Address: P.O. Box 489, Stn. A, Burlington, Ontario, Canada L7R 3Y3
 Shipping Address: 970 Fraser Drive, Burlington, Ontario, Canada L7L 5P5
 Tel. +1 (905) 632-2996 Fax. +1 (905) 632-5946

www.gennum.com

The information contained in this document describes the homogeneous material composition of this product according to the definition set forth in the EU RoHS Directive 2002/95/EC. This information may have been derived from calculations based on information obtained from our suppliers. Gennum Corporation assumes no liability for any errors or omissions in this document. Gennum reserves the right to make changes to this document at any time without notice.