



## Material Composition Sheet

Product: GS9062-CF  
 Package Type: LQFP-80pin  
 Manufacturer: Gennum Corporation

Date: 06-Dec-2006

Component	BOM	Weight of Component (mg)	Substance	Weight of Substance (mg)	Homogeneous Material	
					%	ppm
Die		16.10	Al	0.10	0.62	6211
			Si	16.00	99.37	993789
			Sub-total:	16.10	99.99	1000000
Die Attach	8461H	2.78	1,4butanediolglycidylether	0.17	6.11	61151
			Ag	2.09	75.17	751799
			Amine	0.21	7.55	75540
			Epoxy Resin	0.31	11.15	111511
			Sub-total:	2.78	99.98	1000001
Lead Finish External		19.91	Pb	2.99	15.01	150176
			Sn	16.92	84.98	849824
			Sub-total:	19.91	99.99	1000000
Lead Finish Internal		1.88	Ag	1.88	100.00	1000000
			Sub-total:	1.88	100.00	1000000
Leadframe	Olin 7025	155.10	Cu	149.21	96.20	962025
			Mg	0.23	0.14	1483
			Ni	4.65	2.99	29981
			Si	1.01	0.65	6512
			Sub-total:	155.10	99.98	1000001
Marking Ink	Teca 261	0.02		0.00	0.00	0
			Sub-total:	0.00	0.00	0
Mold Compound	EME 7320	475.20	Antimony Trioxide	7.13	1.50	15004
			BrominatedEpoxyResin	7.13	1.50	15004
			Carbon Black	2.38	0.50	5008
			Epoxy Resin	35.64	7.50	75000
			Phenol Resin	35.64	7.50	75000
			Silica Fused	387.28	81.49	814983
			Sub-total:	475.20	99.99	999999
Wires	MGFL1-B	2.72	Au	2.72	100.00	1000000
			Sub-total:	2.72	100.00	1000000
<b>Total:</b>		<b>673.71</b>				

### GENNUM CORPORATION

Mailing Address: P.O. Box 489, Stn. A, Burlington, Ontario, Canada L7R 3Y3  
 Shipping Address: 970 Fraser Drive, Burlington, Ontario, Canada L7L 5P5  
 Tel. +1 (905) 632-2996 Fax. +1 (905) 632-5946

www.gennum.com

The information contained in this document describes the homogeneous material composition of this product according to the definition set forth in the EU RoHS Directive 2002/95/EC. This information may have been derived from calculations based on information obtained from our suppliers. Gennum Corporation assumes no liability for any errors or omissions in this document. Gennum reserves the right to make changes to this document at any time without notice.